

---

## Product Technical Data Sheet

**75um matt silver PET/ GLASSINE RELEASE  
PAPER**

---

### Facestock

**75um matt silver PET**  
**Thickness(mm) 0.075±0.003**  
**Basis Weight 90g/m<sup>2</sup>**  
**Color Matt silver**

### Adhesive

**SOLVENT GLUE**

### Liner

#### **Glassine release paper**

Thickness(mm)	0.047±0.005
Basis Weight	58±2g/m <sup>2</sup>
Color	White
Transparency	52%

Test Project	Characteristic Value	Unit	Test Method
Spread	20±3	g/ square meter	-----
Adhesive Force	0.8↑	Kn/m	GB/T 2792

<b>Initial Bonding Strength</b>	8	#	GB/T 4852
<b>Endurance Bonding Strength</b>	8	Hours	GB/T 4851
<b>Application Temperature</b>	-10~80	degree celsius	-----

**Shelf life** 24 Month if stored at 22°C and 50% relative humidity

**Precautions for Use:**

1. Best printing processing environment: temperature  $22 \pm 3$  degree celsius, humidity  $55 \% \pm 5$ .
2. When use, please try to be affixed to the surface to remove dirt, oil, water and other impurities.
3. Subjected to an appropriate pressure on the tape, square can achieve sufficient adhesion strength.

**Remark:** All above-mentioned technical information has been recognized as the company uses reliable testing methods, the resulting is an average value after repeated testing, but to ensure the proper selection and use of our products, please basing on the object when you use, firstly use of the purposes and conditions detailed understanding of the trial, or notify us in order to provide you further instructions and services.

**Version**                      **The first edition**                      **Revision date**                      **2025-1-16**